

测试报告

No: SHFDO100811135FDC-1

报告日期: 2010-08-27

客户名称: 宝山钢铁股份有限公司

客户地址: 宝山区长江路 580 号不锈钢大楼 201 室

样品由客户提供及申请者对样品的说明如下:

样品名称: 3Cr14N

批号/生产日期: /

生产商: /

SGS 相关号: SHAFD1011827101

SGS 工作号: SHFDO100811135FD-1

样品接收日期: 2010-08-16

样品测试日期: 2010-08-16 ~ 2010-08-20

测试要求

根据申请者的要求:

按照意大利官方公报(G.U) DMH 1973.03.21 和与接触食品的塑料原料和成品相关的欧盟指令 2002/72/EC (2002/72/EC 修订版本)

(1)材料: 不锈钢

总迁移量进行测试.

(2)材料: 不锈钢

可溶性镍

可溶性铬

测试方法:

1) 参照 EN1186-1:2002 和 EN 1186-3:2002 (全浸没) 重复使用的条件. 结果由第三次萃取得到

2) 参照 EN1186-1:2002 和 EN 1186-3:2002 (全浸没) 重复使用的条件. 结果由第三次萃取得到, 采用 ICP-OES 进行分析

测试结果

请见下页

结论:

所递交的样品符合意大利官方公报(G.U) DMH 1973.03.21 的的要求

注: 以英文制订的本测试报告可以翻译成其它语言, 如有异议, 以英文版为准。

Attention: To check the authenticity of testing /inspection report & certificate, pls. contact tel: (86-755)83071443 email: CN.Doccheck@sgs.com



第 1 页 共 2 页

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



SGS-ITS Standards Technical Services (Shanghai) Co., Ltd.
Testing Center

3rd Building, No. 889, Yishan Road, Shanghai, China 200233
中国·上海·宜山路889号3号楼 邮编: 200233

t (86-21)61402666*2785
t (86-21)61402666*2785

f (86-21)54500454
f (86-21)54500454

SHFD 208343

www.cn.sgs.com
e sgs.china@sgs.com

Member of the SGS Group (SGS SA)

测试报告

No: SHFDO100811135FDC-1

报告日期: 2010-08-27

测试结果

1) 全迁移

常用模拟液	测试条件	测试结果 (mg/dm ²)	最大允许限值 (mg/dm ²)
3% 乙酸	0.5 小时, 100°C	< 3.0	8.0

备注:

(1) 测试结果由第三次萃取结果得出

(2) mg/dm²=毫克每平方米

2) 可溶性镍, 可溶性铬

常用模拟液: 3% 乙酸


测试条件: 0.5 小时, 100°C

测试项目	特殊迁移 (mg/kg)	方法检出限 (mg/kg)	最大允许限值 (mg/kg)
可溶性镍	未检出	0.05	0.1
可溶性铬	未检出	0.05	0.1

备注:

(1) mg/kg = 毫克每千克

样品描述: 银色金属片



*** 报告结束 ***

第 2 页 共 2 页

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



SGS-CTC Standards Technical Services (Shanghai) Co., Ltd.
Testing Center

3rd Building, No. 889, Yishan Road, Shanghai, China 200233
中国·上海·宜山路889号3号楼

t (86-21)61402666*2785
t (86-21)61402666*2785

f (86-21)54500454
f (86-21)54500454

SHFD 208344

www.cn.sgs.com
e sgs.china@sgs.com