

Test Report

No: SHFDO120201517FD-5.2

Date: Feb 28 2012

Client name: BAOSTEEL IRON & STEEL CO., LTD
Client address: No. 580 Changjiang Road, Baoshan Shanghai 200431, China

The following sample(s) was/were submitted by/ on behalf of the client as (except SGS reference No. & SGS job No. & Date of receipt & Testing period):

Sample name: BNDDQ
Batch No./Date: /
Manufacturer: /
SGS reference No.: SHAFD1201805901
SGS job No.: SHFDO120201517FD-5
Date of receipt: Feb 20 2012
Testing period: Feb 20 2012 ~ Feb 27 2012

TEST(S) REQUESTED:

Selected test(s) as requested by applicant:
In accordance with Italian Decree of Ministry of Health of 21/03/1973 and its amendment, Italian Decree of Ministry 21/12/2010, No 258 and Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004.

- (1) For material: Stainless steel - Overall migration test
- (2) For material: stainless steel- Specific migration of Nickel, Chromium and Manganese

TEST METHOD(S):

- (1) With reference to Italian Decree of Ministry of Health of 21/03/1973 and its amendments. Extractive from 3rd duration was taken for analysis.
- (2) Sample preparation in 3% acetic acid at 100° C for 30 minutes with reference to Italian Decree of Ministry of Health of 21/03/1973 and its amendment. Extractive from the 3rd duration was taken for analysis using ICP-OES.

TEST RESULT(S):

Please refer to next page

CONCLUSION:

When tested as specified, the tested parameters comply with the requirements as stated in Italian Decree of Ministry of Health of 21/03/1973 and its amendment, Italian Decree of Ministry 21/12/2010, No 258 and Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004.

Signed for and on behalf of SGS



Page 1 of 2

RAND: 3520814

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



Test Report

No: SHFDO120201517FD-5.2

Date: Feb 28 2012

TEST RESULT(S):


1) Overall migration

Simulant Used	Time	Temperature	Max. Permissible Limit	Result of migration
3% Acetic Acid(W/V)Aqueous Solution	0.5hr	100°C	8mg/dm ²	< 3.0 mg/dm ²

2) Specific migration of Nickel, Chromium and Manganese

Test Item(s)	Limit	Test result(s)	Method Detection Limit(s)
Specific migration of Nickel mg/kg	0.1	Not detected	0.05
Specific migration of Chromium mg/kg	0.1	Not detected	0.05
Specific migration of Manganese mg/kg	0.1	Not detected	0.05

SAMPLE DESCRIPTION: Silvery metal piece



*** End of Report***

