

测试报告

No. SHAEC1210881904

日期: 2012年07月04日 第1页,共3页

宝钢不锈钢有限公司
上海市宝山区长江路735号

以下测试之样品是由申请者所提供及确认: 3Cr14N

SGS工作编号: SP12-019118 - SH
型号: NO.1
样品接收日期: 2012年06月28日
测试周期: 2012年06月28日 - 2012年07月04日
测试要求: 根据客户要求测试
测试方法: 请参见下一页
测试结果: 请参见下一页
结论: 按检测要求, 测试参数符合GB 9684-2011中的要求。

通标标准技术服务有限公司
授权签名



Fan Jingjie, JJ 范晶捷
批准签署人

本报告是发布日期为2012年07月04日编号为SHAEC1210881903 英文检测报告的中文译本。如有异议, 以英文版本为准。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



测试报告

No. SHAEC1210881904

日期: 2012年07月04日 第2页,共3页

测试结果:

测试样品描述:

样品编号	SGS样品ID	描述
1	SHA12-108819.002	银色金属板

感官测试

测试要求: 依照GB 9684-2011进行感官测试.

测试方法: 参考GB 9684-2011方法.

测试项目	限值	002
外观	见备注(1)	阴性

备注:

(1) 阴性=接触食品的表面应光洁,无污垢、锈迹;焊接部应光洁,无气孔,裂缝,毛刺

可溶性铅、镉、镍、铬和砷的含量

测试要求: 依照GB 9684-2011,测定委托样品的可溶性铅、镉、镍、铬和砷的含量.

测试方法: 参考GB 9684-2011方法.

测试项目	限值	单位	MDL	002
可溶铅含量	0.01	mg/dm ²	0.01	ND
可溶镉含量	0.005	mg/dm ²	0.005	ND
可溶镍含量	0.1	mg/dm ²	0.05	ND
可溶铬含量	0.4	mg/dm ²	0.04	ND
可溶砷含量	0.008	mg/dm ²	0.008	ND

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

样品照片:



此照片仅限于随SGS正本报告使用

*** 报告完 ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

